



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Lesley Anne Ezelle  
28228 NE Reilly Road  
Camas, WA 98607 US

Date: 7-Oct-20  
Shear ID:  
Test No: 500936


### Animal and Sample Description

Animal Name: Aoye 2020  
Registry #:  
Breed:  
Sex:  
Colour:

Date of Birth (Age):  
Sample Location: GRID  
Sample Date:  
Previous Shear Date:  
Total Fleece Wt (lbs):

### Laboratory Data

Mean Fiber Diameter:	23.7 microns	Mean Staple Length:	114 mm
Standard Deviation:	4.2 microns	Length Standard Deviation:	7.8 mm
Coefficient of Variation:	17.7 %	Length Coefficient of Variation:	6.8 %
Spin Fineness:	22.5 microns	Mean Curvature:	29.3 deg/mm
Fibers Greater Than 30 microns:	4.8 %	SD Curvature:	19.3 deg/mm
Comfort Factor:	95.2 %	Medullated Fibers:	%



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Jude Davidson  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [nz.wool.timaru@sgs.com](mailto:nz.wool.timaru@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)