



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Moonview Alpaca Farm

Date: 20-Jul-20  
Shear ID: A60  
Test No: 160660


### Animal and Sample Description

Animal Name: Neftic 2018  
Registry #:  
Breed:  
Sex:  
Colour:

Date of Birth (Age):  
Sample Location: GRID  
Sample Date:  
Previous Shear Date:  
Total Fleece Wt (lbs): 0.00

### Laboratory Data

Mean Fiber Diameter:	17.2 microns	Mean Staple Length:	77 mm
Standard Deviation:	3.8 microns	Length Standard Deviation:	2.4 mm
Coefficient of Variation:	22.1 %	Length Coefficient of Variation:	3.1 %
Spin Fineness:	16.9 microns	Mean Curvature:	69.6 deg/mm
Fibers Greater Than 30 microns:	0.7 %	SD Curvature:	37.9 deg/mm
Comfort Factor:	99.3 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Jude Davidson  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [nz.wool.timaru@sgs.com](mailto:nz.wool.timaru@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)