


# DOUBLE BARREL

**AFD:** 19.5  $\mu$   
**SD:** 3.4  $\mu$   
**CV:** 17.5 %  
**CF:** 99.4 %  
**Curve:** 51.3 Dg/mm  
**Min:** 17.6  $\mu$   
**Max:** 21.3  $\mu$   
**Staple:** 95.0 mm

% of Fibers



*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# DOUBLE BARREL

**AFD:** 19.5  $\mu$   
**SD:** 3.4  $\mu$   
**CV:** 17.5 %  
**CF:** 99.4 %  
**Curve:** 51.3 Dg/mm  
**Min:** 17.6  $\mu$   
**Max:** 21.3  $\mu$   
**Staple:** 95.0 mm

