


AFD: 23.7 μ
SD: 5.6 μ
CV: 23.5 %
CF: 87.6 %
Curve: 26.7 Dg/mm
Min: 20.3 μ
Max: 28.1 μ
Staple: 130.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

LBCA'S JET

AFD: 23.7 μ
SD: 5.6 μ
CV: 23.5 %
CF: 87.6 %
Curve: 26.7 Dg/mm
Min: 20.3 μ
Max: 28.1 μ
Staple: 130.0 mm

