



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Olde Lyfe
6150 Franktown Rd
Carson City NV, US

Date: 6-Oct-23
Shear ID: 257784
Test No: 615590


Animal and Sample Description

Animal Name: BRONZED MOKA
Registry #: 35388470
Breed: Huacaya
Sex: Male
Colour: 205 - Dark Fawn

Date of Birth (Age): 12-Jul-18
Sample Location: GRID
Sample Date: 6-Jun-23
Previous Shear Date: 19-May-22
Total Fleece Wt (lbs): 5.90

Laboratory Data

Mean Fiber Diameter:	21.7 microns	Mean Staple Length:	96 mm
Standard Deviation:	5.8 microns	Length Standard Deviation:	4.3 mm
Coefficient of Variation:	26.7 %	Length Coefficient of Variation:	4.5 %
Spin Fineness:	22.3 microns	Mean Curvature:	53.5 deg/mm
Fibers Greater Than 30 microns:	5.4 %	SD Curvature:	39.0 deg/mm
Comfort Factor:	94.6 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com