



Optical Fiber Diameter Analyser (OFDA100)
Micron Test Report

Briarwood Acres
4150 Briarwood NW St
OR 97304-9541, US

Date: 20-Oct-22
Shear ID: 243630
Test No: 610440


Animal and Sample Description

Animal Name: Eldora's Yukon By Tempo
Registry #: 35388517
Breed: Suri
Sex: Male
Colour: 204 - Medium Fawn

Date of Birth (Age): 17-Jun-18
Sample Location: GRID
Sample Date: 24-Jun-22
Previous Shear Date: 23-May-21
Total Fleece Wt (lbs): 7.5

Laboratory Data

Mean Fiber Diameter:	31.4 microns	Mean Staple Length:	168 mm
Standard Deviation:	6.6 microns	Length Standard Deviation:	6.8 mm
Coefficient of Variation:	20.9 %	Length Coefficient of Variation:	4.0 %
Spin Fineness:	30.5 microns	Mean Curvature:	27.4 deg/mm
Fibers Greater Than 30 microns:	52.6 %	SD Curvature:	11.6 deg/mm
Comfort Factor:	47.4 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below
SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com