



### Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Brianwood Acres  
4150 Briarwood NW St  
OR 97304-9541, US

Date: 20-Oct-22  
Shear ID: 243632  
Test No: 610442


#### Animal and Sample Description

Animal Name: Sssa Accoyo Edan's Eve  
Registry #: 35422983  
Breed: Suri  
Sex: Female  
Colour: 202 - Light Fawn

Date of Birth (Age): 25-Jul-16  
Sample Location: GRID  
Sample Date: 24-Jun-22  
Previous Shear Date: 23-May-21  
Total Fleece Wt (lbs): 5.0625

#### Laboratory Data

Mean Fiber Diameter:	28.2 microns	Mean Staple Length:	156 mm
Standard Deviation:	6.4 microns	Length Standard Deviation:	4.4 mm
Coefficient of Variation:	22.6 %	Length Coefficient of Variation:	2.8 %
Spin Fineness:	27.8 microns	Mean Curvature:	27.3 deg/mm
Fibers Greater Than 30 microns:	28.9 %	SD Curvature:	9.4 deg/mm
Comfort Factor:	71.1 %	Medullated Fibers:	26.9 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)