



Optical Fiber Diameter Analyser (OFDA100)  
Micron Test Report

Briarwood Acres  
4150 Briarwood NW St  
OR 97304-9541, US

Date: 20-Oct-22  
Shear ID: 243626  
Test No: 610436


Animal and Sample Description

Animal Name: Briarwood's Amazing Grace By Bravo  
Registry #: 35603399  
Breed: Suri  
Sex: Female  
Colour: 204 - Medium Fawn

Date of Birth (Age): 5-Aug-19  
Sample Location: GRID  
Sample Date: 24-Jun-22  
Previous Shear Date: 23-May-21  
Total Fleece Wt (lbs): 7.0625

Laboratory Data

Mean Fiber Diameter:	28.5 microns	Mean Staple Length:	171 mm
Standard Deviation:	5.1 microns	Length Standard Deviation:	12.3 mm
Coefficient of Variation:	17.7 %	Length Coefficient of Variation:	7.2 %
Spin Fineness:	27.0 microns	Mean Curvature:	27.1 deg/mm
Fibers Greater Than 30 microns:	31.9 %	SD Curvature:	9.2 deg/mm
Comfort Factor:	68.1 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kibimie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)