



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Briarwood Acres
4150 Briarwood NW St
OR 97304-9541, US

Date: 20-Oct-22
Shear ID: 243633
Test No: 610443


Animal and Sample Description

Animal Name: Talent's Toscanini Of 2Pointfarm
Registry #: 35179979
Breed: Suri
Sex: Male
Colour: 100 - White

Date of Birth (Age): 12-Jun-17
Sample Location: GRID
Sample Date: 24-Jun-22
Previous Shear Date: 26-Apr-21
Total Fleece Wt (lbs): 10.125

Laboratory Data

Mean Fiber Diameter:	36.1 microns	Mean Staple Length:	181 mm
Standard Deviation:	7.8 microns	Length Standard Deviation:	11.6 mm
Coefficient of Variation:	21.7 %	Length Coefficient of Variation:	6.4 %
Spin Fineness:	35.3 microns	Mean Curvature:	26.8 deg/mm
Fibers Greater Than 30 microns:	77.6 %	SD Curvature:	10.6 deg/mm
Comfort Factor:	22.4 %	Medullated Fibers:	79.1 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below
SGS NZ LTD - 48 Kemp Street, Kilmire 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com