



**Optical Fiber Diameter Analyser (OFDA100)  
Micron Test Report**

Briarwood Acres  
4150 Briarwood NW St  
OR 97304-9541, US

Date: 20-Oct-22  
Shear ID: 243628  
Test No: 610438


**Animal and Sample Description**

Animal Name: Briarwood's Patience By Bronx  
Registry #: 35523444  
Breed: Suri  
Sex: Female  
Colour: 204 - Medium Fawn

Date of Birth (Age): 23-Jun-19  
Sample Location: GRID  
Sample Date: 24-Jun-22  
Previous Shear Date: 23-May-21  
Total Fleece Wt (lbs): 7.0625

**Laboratory Data**

Mean Fiber Diameter:	34.5 microns	Mean Staple Length:	147 mm
Standard Deviation:	9.3 microns	Length Standard Deviation:	4.3 mm
Coefficient of Variation:	26.9 %	Length Coefficient of Variation:	2.9 %
Spin Fineness:	35.4 microns	Mean Curvature:	27.1 deg/mm
Fibers Greater Than 30 microns:	64.0 %	SD Curvature:	8.2 deg/mm
Comfort Factor:	36.0 %		



**Test Performed According to Method AS/NZS 4492.5:2000**

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)