



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Briarwood Acres
4150 Briarwood Street, Salem
NH, 97304 US

Date: 30-Jul-21
Shear ID: 222570
Test No: 603396


Animal and Sample Description

Animal Name: Briarwood's Ginger Lily by Bronx
Registry #: 35523567
Breed: Suri
Sex: Female
Colour: 410 - Dark Brown

Date of Birth (Age): 31-May-19
Sample Location: GRID
Sample Date: 23-May-21
Previous Shear Date: 30-May-20
Total Fleece Wt (lbs): 7.00

Laboratory Data

Mean Fiber Diameter:	24.0 microns	Mean Staple Length:	193 mm
Standard Deviation:	6.4 microns	Length Standard Deviation:	20.6 mm
Coefficient of Variation:	26.7 %	Length Coefficient of Variation:	10.7 %
Spin Fineness:	24.6 microns	Mean Curvature:	28.1 deg/mm
Fibers Greater Than 30 microns:	11.8 %	SD Curvature:	12.4 deg/mm
Comfort Factor:	88.2 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below
SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com