



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Elizabeth Turner
15414 140th St, Foreston
MN 56330-9541, US

Date: 11-Aug-23
Shear ID: 253010
Test No: 614098


Animal and Sample Description

Animal Name: TTA Concerto by Amadeus
Registry #: 36115266
Breed: Huacaya
Sex: Male
Colour: 100 - White

Date of Birth (Age): 27-Apr-20
Sample Location: GRID
Sample Date: 3-May-23
Previous Shear Date: 19-May-22
Total Fleece Wt (lbs): 12

Laboratory Data

Mean Fiber Diameter:	20.0 microns	Mean Staple Length:	91 mm
Standard Deviation:	4.6 microns	Length Standard Deviation:	3.3 mm
Coefficient of Variation:	23.0 %	Length Coefficient of Variation:	3.7 %
Spin Fineness:	19.8 microns	Mean Curvature:	50.1 deg/mm
Fibers Greater Than 30 microns:	2.9 %	SD Curvature:	24.5 deg/mm
Comfort Factor:	97.1 %	Medullated Fibers:	18.9 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com