



Yocom-McColl Testing Laboratories, Inc.

540 West Elk Place • Denver, Colorado 80216-1823 USA

PHONE (303) 294-0582 • FAX (303) 295-6944

EMAIL: ymccoll@ymccoll.com

Sirolan Laserscan Micron Test Report

Golden Pine Alpacas/Barbara Patterson
163 Golden Pine
Goldendale WA 98620

06/10/14

Test No: 479461


Animal and Sample Description

Animal Name: Janus Navigational Beacon
Breed: Alpaca(Huacaya)
Sex: Female
Color: Dark Silver Grey

Animal ID: 31523011
Sample Location: Side
Sample Date: 05/14/14
Age: 07/28/09

Laboratory Data

Mean Fiber Diameter: 23.4 microns
Standard Deviation: 5.0 microns
Coefficient of Variation: 21.2 %
Fibers Greater Than 30 microns: 9.1 %



This Test Performed According to I.W.T.O Method 12



Yocom-McColl Testing Laboratories, Inc.

540 West Elk Place • Denver, Colorado 80216-1823 USA

PHONE (303) 294-0582 • FAX (303) 295-6944

EMAIL: ymccoll@ymccoll.com

Sirolan Laserscan Micron Test Report

Golden Pine Alpacas/Barbara Patterson
163 Golden Pine
Goldendale WA 98620

06/10/14

Test No: 479460


Animal and Sample Description

Animal Name: Golden Pine's Victoria
Breed: Alpaca(Huacaya)
Sex: Female
Color: Dark Fawn

Animal ID: 32728743
Sample Location: Side
Sample Date: 05/15/14
Age: 09/25/13

Laboratory Data

Mean Fiber Diameter: 19.4 microns
Standard Deviation: 4.1 microns
Coefficient of Variation: 21.3 %
Fibers Greater Than 30 microns: 1.9 %



This Test Performed According to I.W.T.O Method 12



Yocom-McColl Testing Laboratories, Inc.

540 West Elk Place • Denver, Colorado 80216-1823 USA

PHONE (303) 294-0582 • FAX (303) 295-6944

EMAIL: ymccoll@ymccoll.com

Sirolan Laserscan Micron Test Report

Golden Pine Alpacas/Barbara Patterson
163 Golden Pine
Goldendale WA 98620

06/10/14

Test No: 479459


Animal and Sample Description

Animal Name: Golden Pine's Tyler
Breed: Alpaca(Huacaya)
Sex: Male
Color: Dark Brown

Animal ID: 32304602
Sample Location: Side
Sample Date: 05/14/14
Age: 08/10/13

Laboratory Data

Mean Fiber Diameter: 17.8 microns
Standard Deviation: 3.1 microns
Coefficient of Variation: 17.3 %
Fibers Greater Than 30 microns: 0.5 %



This Test Performed According to I.W.T.O Method 12



Yocom-McColl Testing Laboratories, Inc.

540 West Elk Place • Denver, Colorado 80216-1823 USA

PHONE (303) 294-0582 • FAX (303) 295-6944

EMAIL: ymccoll@ymccoll.com

Sirolan Laserscan Micron Test Report

Golden Pine Alpacas/Barbara Patterson
163 Golden Pine
Goldendale WA 98620

06/10/14

Test No: 479458


Animal and Sample Description

Animal Name: Golden Pine's Tania
Breed: Alpaca(Huacaya)
Sex: Female
Color: Light Fawn

Animal ID: 31903103
Sample Location: Side
Sample Date: 05/14/14
Age: 09/03/11

Laboratory Data

Mean Fiber Diameter: 19.1 microns
Standard Deviation: 3.8 microns
Coefficient of Variation: 19.7 %
Fibers Greater Than 30 microns: 0.9 %



This Test Performed According to I.W.T.O Method 12