


# WRSR KAZMERE BY FUSION

**AFD:** 22.0  $\mu$   
**SD:** 5.2  $\mu$   
**CV:** 23.4 %  
**CF:** 95.0 %  
**Curve:** 14.7 Dg/mm  
**Min:** 16.3  $\mu$   
**Max:** 26.0  $\mu$   
**Staple:** 0.0 mm


% of Fibers

*Alpaca Fiber Testing USA*



# WRSR KAZMERE BY FUSION

**AFD:** 22.0  $\mu$   
**SD:** 5.2  $\mu$   
**CV:** 23.4 %  
**CF:** 95.0 %  
**Curve:** 14.7 Dg/mm  
**Min:** 16.3  $\mu$   
**Max:** 26.0  $\mu$   
**Staple:** 0.0 mm



*Alpaca Fiber Testing USA*