


WSR JACKKNIFE BY FUSION

AFD: 22.3 μ
SD: 4.8 μ
CV: 21.3 %
CF: 94.1 %
Curve: 12.7 Dg/mm
Min: 20.2 μ
Max: 24.7 μ
Staple: 130.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

WSR JACKKNIFE BY FUSION

AFD: 22.3 μ
SD: 4.8 μ
CV: 21.3 %
CF: 94.1 %
Curve: 12.7 Dg/mm
Min: 20.2 μ
Max: 24.7 μ
Staple: 130.0 mm

