


AFD: 32.2 μ
SD: 6.6 μ
CV: 20.4 %
CF: 46.2 %
Curve: 11.5 Dg/mm
Min: 31.5 μ
Max: 33.6 μ
Staple: 120.0 mm

% of Fibers

Alpaca Fiber Testing USA



Fiber Diameter (microns)

AFD: 32.2 μ
SD: 6.6 μ
CV: 20.4 %
CF: 46.2 %
Curve: 11.5 Dg/mm
Min: 31.5 μ
Max: 33.6 μ
Staple: 120.0 mm

