



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Liberty Alpacas

Date: 20-Jul-20
Shear ID: A74
Test No: 160674


Animal and Sample Description

Animal Name: LibertyAlpacas Let Freedom Ring
Registry #: 35578581
Breed:
Sex:
Colour:

Date of Birth (Age): 30-May-19
Sample Location: GRID
Sample Date: 16-May-20
Previous Shear Date:
Total Fleece Wt (lbs): 0.00

Laboratory Data

Mean Fiber Diameter:	16.6 microns	Mean Staple Length:	95 mm
Standard Deviation:	3.1 microns	Length Standard Deviation:	3.4 mm
Coefficient of Variation:	18.4 %	Length Coefficient of Variation:	3.5 %
Spin Fineness:	15.8 microns	Mean Curvature:	51.5 deg/mm
Fibers Greater Than 30 microns:	0.2 %	SD Curvature:	28.9 deg/mm
Comfort Factor:	99.8 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com