



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sunny Alpacas
9200 Spooner Creek Ln
Blaine, WA 98230 US

Date: 26-Jul-20
Shear ID:
Test No: 200712


Animal and Sample Description

Animal Name: Sunny Premier Semiahmoo
Registry #: 35578307
Breed: Huacaya
Sex: Male
Colour: 100 - White

Date of Birth (Age): 07/13/2019
Sample Location: GRID
Sample Date:
Previous Shear Date: 25-Aug-19
Total Fleece Wt (lbs): 4.54

Laboratory Data

Mean Fiber Diameter:	17.4 microns	Mean Staple Length:	100 mm
Standard Deviation:	3.3 microns	Length Standard Deviation:	4.8 mm
Coefficient of Variation:	18.8 %	Length Coefficient of Variation:	4.8 %
Spin Fineness:	16.6 microns	Mean Curvature:	46.2 deg/mm
Fibers Greater Than 30 microns:	0.5 %	SD Curvature:	25.9 deg/mm
Comfort Factor:	99.5 %	Medullated Fibers:	10.8 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com