



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sunny Alpacas
9200 Spooner Creek Ln
Blaine, WA 98230 US

Date: 27-Jul-20
Shear ID:
Test No: 200760


Animal and Sample Description

Animal Name: SA ACCOYO CABELLA
Registry #: 32065152
Breed: Huacaya
Sex: Female
Colour: 205 - Dark Fawn

Date of Birth (Age): 04/23/2010
Sample Location: GRID
Sample Date:
Previous Shear Date: 11-Jun-19
Total Fleece Wt (lbs): 3.39

Laboratory Data

Mean Fiber Diameter:	18.0 microns	Mean Staple Length:	59 mm
Standard Deviation:	4.1 microns	Length Standard Deviation:	1.8 mm
Coefficient of Variation:	22.6 %	Length Coefficient of Variation:	3.0 %
Spin Fineness:	17.8 microns	Mean Curvature:	44.1 deg/mm
Fibers Greater Than 30 microns:	1.2 %	SD Curvature:	26.1 deg/mm
Comfort Factor:	98.8 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com