



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sunny Alpacas
9200 Spooner Creek Ln
Blaine, WA 98230 US

Date: 27-Jul-20
Shear ID:
Test No: 200763


Animal and Sample Description

Animal Name: Sunny Accoyo Cherokee
Registry #: 35532316
Breed: Huacaya
Sex: Female
Colour: 306 - Dark Rose Grey

Date of Birth (Age): 07/15/2019
Sample Location: GRID
Sample Date:
Previous Shear Date: 31-Aug-19
Total Fleece Wt (lbs): 3.68

Laboratory Data

Mean Fiber Diameter:	19.1 microns	Mean Staple Length:	75 mm
Standard Deviation:	4.3 microns	Length Standard Deviation:	2.6 mm
Coefficient of Variation:	22.2 %	Length Coefficient of Variation:	3.5 %
Spin Fineness:	18.8 microns	Mean Curvature:	52.3 deg/mm
Fibers Greater Than 30 microns:	1.9 %	SD Curvature:	25.5 deg/mm
Comfort Factor:	98.1 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com