



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

JEFF HASELHORST AND_OR LISA HASEL HORST
12102 N 1st St
Parker, CO 80134-9638 US

Date: 20-Aug-20
Shear ID: 200638
Test No: 200294


Animal and Sample Description

Animal Name: GOLDEN RAE's Nahara
Registry #: 35493372
Breed: Suri
Sex: Female
Colour: 201 - Beige

Date of Birth (Age): 20-Aug-18
Sample Location: GRID
Sample Date: 13-Jun-20
Previous Shear Date: 8-Jun-19
Total Fleece Wt (lbs): 10.10

Laboratory Data

Mean Fiber Diameter:	20.7 microns	Mean Staple Length:	197 mm
Standard Deviation:	5.8 microns	Length Standard Deviation:	26.1 mm
Coefficient of Variation:	27.7 %	Length Coefficient of Variation:	13.3 %
Spin Fineness:	21.5 microns	Mean Curvature:	14.3 deg/mm
Fibers Greater Than 30 microns:	6.4 %	SD Curvature:	24.4 deg/mm
Comfort Factor:	93.6 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com