



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

STACEY SUZANNE PAYNE
500 Cleveland St
Fallon, NV 89406-4002 US

Date: 26-Aug-20
Shear ID: 204032
Test No: 200561


Animal and Sample Description

Animal Name: BRONZED MOKA
Registry #: 35388470
Breed: Huacaya
Sex: Male
Colour: 205 - Dark Fawn

Date of Birth (Age): 12-Jul-18
Sample Location: GRID
Sample Date: 19-Jun-20
Previous Shear Date: 15-May-19
Total Fleece Wt (lbs): 3.80

Laboratory Data

Mean Fiber Diameter:	18.5 microns	Mean Staple Length:	90 mm
Standard Deviation:	3.5 microns	Length Standard Deviation:	7.6 mm
Coefficient of Variation:	18.9 %	Length Coefficient of Variation:	8.4 %
Spin Fineness:	17.7 microns	Mean Curvature:	47.8 deg/mm
Fibers Greater Than 30 microns:	0.4 %	SD Curvature:	25.4 deg/mm
Comfort Factor:	99.6 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com