



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Knolveston Farm LLC  
233 Bartlett  
Weaverville, AL 28787 US

Date: 7-Oct-20  
Shear ID:  
Test No: 500926


### Animal and Sample Description

Animal Name: Knolveston's Beta Max  
Registry #: 36016815  
Breed:  
Sex:  
Colour: 204 - Medium Fawn

Date of Birth (Age):  
Sample Location: GRID  
Sample Date: 13-May-20  
Previous Shear Date: 10-Apr-19  
Total Fleece Wt (lbs):

### Laboratory Data

Mean Fiber Diameter:	15.5 microns	Mean Staple Length:	153 mm
Standard Deviation:	3.8 microns	Length Standard Deviation:	13.4 mm
Coefficient of Variation:	24.3 %	Length Coefficient of Variation:	8.7 %
Spin Fineness:	15.5 microns	Mean Curvature:	14.0 deg/mm
Fibers Greater Than 30 microns:	0.7 %	SD Curvature:	16.4 deg/mm
Comfort Factor:	99.3 %	Medullated Fibers:	%



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Jude Davidson  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [nz.wool.timaru@sgs.com](mailto:nz.wool.timaru@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)