


# RAYNAY'S MAJESTIC PRINCE BY TEMPO

**AFD:** 19.1  $\mu$   
**SD:** 4.6  $\mu$   
**CV:** 23.8 %  
**CF:** 98.0 %  
**Curve:** 18.6 Dg/mm  
**Min:** 17.0  $\mu$   
**Max:** 21.9  $\mu$   
**Staple:** 140.0 mm

% of Fibers

*Alpaca Fiber Testing USA*



Fiber Diameter (microns)

# RAYNAY'S MAJESTIC PRINCE BY TEMPO

**AFD:** 19.1  $\mu$   
**SD:** 4.6  $\mu$   
**CV:** 23.8 %  
**CF:** 98.0 %  
**Curve:** 18.6 Dg/mm  
**Min:** 17.0  $\mu$   
**Max:** 21.9  $\mu$   
**Staple:** 140.0 mm

