



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

FLYING IRON RANCH ALPACAS  
9110 Rockbrook Dr  
Dallas, TX 7520-3907 US

Date: 20-Aug-20  
Shear ID: 205198  
Test No: 200317


### Animal and Sample Description

Animal Name: FIR TERRA OF CORSAIR  
Registry #: 35132431  
Breed: Huacaya  
Sex: Female  
Colour: 100 - White

Date of Birth (Age): 7-Aug-17  
Sample Location: GRID  
Sample Date: 26-May-20  
Previous Shear Date: 8-May-19  
Total Fleece Wt (lbs): 9.20

### Laboratory Data

Mean Fiber Diameter:	20.2 microns	Mean Staple Length:	104 mm
Standard Deviation:	3.8 microns	Length Standard Deviation:	0.5 mm
Coefficient of Variation:	18.8 %	Length Coefficient of Variation:	0.5 %
Spin Fineness:	19.3 microns	Mean Curvature:	38.9 deg/mm
Fibers Greater Than 30 microns:	0.9 %	SD Curvature:	19.2 deg/mm
Comfort Factor:	99.1 %	Medullated Fibers:	6.3 %



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Jude Davidson  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [nz.wool.timaru@sgs.com](mailto:nz.wool.timaru@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)