


AFD: 22.2 μ
SD: 4.8 μ
CV: 21.8 %
CF: 93.7 %
Curve: 49.4 Dg/mm
Min: 21.0 μ
Max: 23.6 μ
Staple: 70.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

RR COCO CHANEL

AFD: 22.2 μ
SD: 4.8 μ
CV: 21.8 %
CF: 93.7 %
Curve: 49.4 Dg/mm
Min: 21.0 μ
Max: 23.6 μ
Staple: 70.0 mm

