



**AFD:** 17.9  $\mu$   
**SD:** 4.0  $\mu$   
**CV:** 22.2 %  
**CF:** 99.8 %  
**Curve:** 44.8 Dg/mm  
**Min:** 16.8  $\mu$   
**Max:** 19.7  $\mu$   
**Staple:** 75.0 mm



# RR CONTESSA

**AFD:** 17.9  $\mu$   
**SD:** 4.0  $\mu$   
**CV:** 22.2 %  
**CF:** 99.8 %  
**Curve:** 44.8 Dg/mm  
**Min:** 16.8  $\mu$   
**Max:** 19.7  $\mu$   
**Staple:** 75.0 mm



*Alpaca Fiber Testing USA*