



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sunny Alpacas
9200 Spooner Creek Ln
Blaine, WA 98230 US

Date: 27-Jul-20
Shear ID:
Test No: 200744


Animal and Sample Description

Animal Name: Sunny Accoyo Lauren
Registry #: 35486305
Breed: Huacaya
Sex: Female
Colour: 202 - Light Fawn

Date of Birth (Age): 07/26/2018
Sample Location: GRID
Sample Date:
Previous Shear Date: 11-Jun-19
Total Fleece Wt (lbs): 5.83

Laboratory Data

Mean Fiber Diameter:	20.6 microns	Mean Staple Length:	95 mm
Standard Deviation:	3.5 microns	Length Standard Deviation:	5.4 mm
Coefficient of Variation:	16.9 %	Length Coefficient of Variation:	5.7 %
Spin Fineness:	19.4 microns	Mean Curvature:	55.4 deg/mm
Fibers Greater Than 30 microns:	0.7 %	SD Curvature:	26.7 deg/mm
Comfort Factor:	99.3 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com