



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Memory M-Acres

Date: 25-Sep-20
Shear ID: 204382
Test No: 500639


Animal and Sample Description

Animal Name: MACRES Silver Sunrise by Vader
Registry #: 35562061
Breed: Suri
Sex: Female
Colour: 410 - Dark Brown

Date of Birth (Age): 17-Apr-19
Sample Location: GRID
Sample Date: 27-Apr-20
Previous Shear Date:
Total Fleece Wt (lbs): 5.06

Laboratory Data

Mean Fiber Diameter:	19.3 microns	Mean Staple Length:	179 mm
Standard Deviation:	4.3 microns	Length Standard Deviation:	20.4 mm
Coefficient of Variation:	22.1 %	Length Coefficient of Variation:	11.4 %
Spin Fineness:	19.0 microns	Mean Curvature:	9.4 deg/mm
Fibers Greater Than 30 microns:	2.1 %	SD Curvature:	16.7 deg/mm
Comfort Factor:	97.9 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com