



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Memory M-Acres

Date: 25-Sep-20
Shear ID: 204370
Test No: 500647


Animal and Sample Description

Animal Name: MMALP GOLDSTAR'S VADER
Registry #: 35064183
Breed: Suri
Sex: Male
Colour: 500 - True Black

Date of Birth (Age): 5-Nov-13
Sample Location: GRID
Sample Date: 27-Apr-20
Previous Shear Date: 19-Apr-19
Total Fleece Wt (lbs): 7.13

Laboratory Data

Mean Fiber Diameter:	25.6 microns	Mean Staple Length:	118 mm
Standard Deviation:	5.5 microns	Length Standard Deviation:	5.4 mm
Coefficient of Variation:	21.6 %	Length Coefficient of Variation:	4.6 %
Spin Fineness:	25.1 microns	Mean Curvature:	8.5 deg/mm
Fibers Greater Than 30 microns:	18.1 %	SD Curvature:	13.2 deg/mm
Comfort Factor:	81.9 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool@sgs.com Web: www.wooltesting.sgs.com