



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Rhonda Deschner
PO Box 919, Wimberley
TX 78676, US

Date: 10-Jun-22
Shear ID: 234650
Test No: 607540


Animal and Sample Description

Animal Name: TP Belladora
Registry #: 35456766
Breed: Huacaya
Sex: Female
Colour: 100 - White

Date of Birth (Age): 7-Jan-21
Sample Location: GRID
Sample Date: 10-May-22
Previous Shear Date: 15-Jun-21
Total Fleece Wt (lbs): 5.9

Laboratory Data

Mean Fiber Diameter:	16.2 microns	Mean Staple Length:	112 mm
Standard Deviation:	3.1 microns	Length Standard Deviation:	2.8 mm
Coefficient of Variation:	18.9 %	Length Coefficient of Variation:	2.5 %
Spin Fineness:	15.5 microns	Mean Curvature:	54.9 deg/mm
Fibers Greater Than 30 microns:	0.3 %	SD Curvature:	21.9 deg/mm
Comfort Factor:	99.7 %	Medullated Fibers:	1.0 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com