


AFD: 26.2 μ
SD: 6.0 μ
CV: 22.8 %
CF: 80.3 %
Curve: 29.5 Dg/mm
Min: 24.0 μ
Max: 28.5 μ
Staple: 115.0 mm

% of Fibers

Alpaca Fiber Testing USA



Fiber Diameter (microns)

SAVANAH

AFD: 26.2 μ
SD: 6.0 μ
CV: 22.8 %
CF: 80.3 %
Curve: 29.5 Dg/mm
Min: 24.0 μ
Max: 28.5 μ
Staple: 115.0 mm

