



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

STACEY SUZANNE PAYNE
500 Cleveland St
Fallon, NV 89406-4002 US

Date: 26-Aug-20
Shear ID: 204027
Test No: 200556


Animal and Sample Description

Animal Name: 4-SIGHTS STALLONE
Registry #: 35095651
Breed: Huacaya
Sex: Male
Colour: 500 - True Black

Date of Birth (Age): 30-May-16
Sample Location: GRID
Sample Date: 17-Apr-20
Previous Shear Date: 30-May-19
Total Fleece Wt (lbs): 4.60

Laboratory Data

Mean Fiber Diameter:	23.8 microns	Mean Staple Length:	79 mm
Standard Deviation:	4.8 microns	Length Standard Deviation:	2.6 mm
Coefficient of Variation:	20.2 %	Length Coefficient of Variation:	3.3 %
Spin Fineness:	23.0 microns	Mean Curvature:	35.4 deg/mm
Fibers Greater Than 30 microns:	8.2 %	SD Curvature:	19.1 deg/mm
Comfort Factor:	91.8 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com